

Updated: 10.02.2025



FIX & SEAL

Product package	310 ml cartridge
Colors	White, Black, Grey
Description	Hybrid polymer compound, elastic, neutral and moisture-drying 1-component multipurpose adhesive and sealant.

TECHNICAL DATA

Base	Hybrid-polymer
Composition	Paste-like substance
Joint movement	Max ± 20 %
Density	Approx. 1,6 g/ml
Elongation at break	(ISO 37) 400 %
Tensile strength	(ISO 37) 1,5 N/mm ²
Hardness	40 \pm 5 Shore A
100% Modulus	(ISO 37) approx. 0,80 N/mm ²
Skin formation	Approx. 10 min (+23°C / 50% RH)
Drying time	Approx. 3 mm/vrk (+23°C / 50% RH)
Operating temperature	+5°C...+35°C degrees
Temperature resistance	After drying -40°C...+90°C degrees
Cleaning	As fresh with mineral spirit. As cured only mechanically or with a silicon remover.
Shelf life	12 month in an unopened packaging
Storage	Protected from frost at +5°C...+25°C degrees.
Yield	Approx. 3,1 m / 10x10 mm joint. Width of joint mm* depth of joint mm= ml/m

Continues on the next page...

Updated: 10.02.2025



NOTE!

- Not suitable for aquarium or swimming pool use, PMMA (Nylon), PTFE, PE, PP, Polycarbonate, Teflon or bitumen surfaces or copper surfaces/bronze and brass.
- Initial testing on powder-coated aluminum or steel is recommended. When needed you must be prepared to use primer.
- It is not recommended to be used on surfaces that have or can come off wax, tar, butyl, neoprene or paraffin. Not for permanent water immersion. Not for glazing.
- Bonding plastics such as PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) under stress can cause cracking in these substrates.

FEATURES

- Easy to use and finish in all weather conditions
- No odour
- Stays elastic after curing
- Mold protected
- Adheres firmly to most materials without primer, e.g. porous materials
- UV resistant, but a complete UV light deficiency can cause colour change. The color change does not change the other properties of the product.
- Good aging resistance
- Very good moisture resistance
- Can be painted over with water-based paints (pre-test recommended)
- Does not contain solvents, halogens or isocyanate or phthalates, completely neutral
- Suitable for natural stone

USE

-All normal construction work where high movement ability and movement joints between different materials are required

- Movement joints
- Sealing of window and door frames
- Jointing and sealing of prefabricated elements

Suitable for all common building materials. The surfaces must be clean, dry, grease-free and dust-free. Porous surfaces should be primed. Non-porous surfaces should at least be cleaned well.

We always recommend a test on surfaces before use.

Continues on the next page...



Updated: 10.02.2025

Cut the cartridge top open and attach the nozzle to the threads. Cut the beak diagonally to fit the joint. Dispense the product into the joint with a cartridge gun and finish the surface using soapy water and a jointing tool or your finger before skin formation. Marking the limits with masking tape makes working easier.

JOINT DIMENSIONS

Min. width for bonding: 2 mm

Min. width for joints: 5 mm

Max. width for bonding: 10 mm

Max. width for joints: 30 mm

Min. depth for joints: 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

CHEMICAL RESISTANCE

Good against: water, seawater, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, dilute acids and bases.

Poor against: aromatic solvents, concentrated acids and chlorinated hydrocarbons.