SILICONE SPRAY MX-300

EN

1 / 1

TECHNICAL DATASHEET

TDS

Updated: 14.07.2022



SILICONE SPRAY MX-300	
Package sizes	400ml
Description	High quality silicone spray to lubricate and protect plastic and rubber parts.
TECHNICAL DATA	
Composition	Silicone polymer
Color	Clear/transparent
Odor	Characteristic
VOC content	Approx. 88 %
Relative density (20°C)	0,72 g/ml
Pressure (20°C)	3–4 bar
Refractive index (25°C)	1,403
Disruptive strength (20°C)	14 kv/mm
Resistance	4 x 1015 Ohm/cm
Temperature resistance	-50°C ... +200°C
pH-value	Neutral
Shelf-life	10 years

FEATURES

- Excellent adhesion
- Moisture displacing effect
- Prevents rubber surfaces from drying out and freezing
- Prevents creaking and screeching of plastic surfaces
- Excellent mechanical and heat resistance
- Resists different weather conditions
- Water-resistant
- Resistant to dilutes acids and bases
- Precise straw nozzle

USAGE

The aerosol should be at room temperature. The operating temperature should be +5°C ... +30°C. Shake before use. Apply a thin layer to the area to be treated. Optimal lubrication is achieved when the solvent has evaporated.

RAKENNUSKEMIA

Kerkkolankatu 17
05800 HYVINKÄÄ
FINLAND

info@rakennuskemia.com
www.rakennuskemia.com
+358 - 19 - 457 4400