

# WTF® D4 WOOD GLUE

Updated: 23.01.2025





WTF <sup>®</sup> D4 WOOD GLUE	
Package size	250 ml
Color	white
Description	D4 Wood Glue is a ready to use PVAc-based wood adhesive with excellent water resistance (D4).
TECHNICAL INFORMATION	
Basis	PVAc
Consistency	High viscous fluid
Curing system	Physical drying
Density	Ca. 1,10 g/ml
Viscosity (Brookfield)	5.000 mPa.s $\rightarrow$ 7.000 mPa.s
Temperature resistance**	-20 °C +80 °C
Total solid content	Ca. 50 %
Open time*	Ca. 8 min.
Pressing pressure	$1 \text{ kg/cm}^2 \rightarrow 2 \text{ kg/cm}^2$
Pressing times	See Use
Water resistance (EN204)	D4
Application temperature	+15 °C +35 °C
pH level	2,5 3,5
Min. Film Forming Temperature (MFFT)	+15 °C
Consumption*	80 - 140 g/m² in full surface bonding. 160 - 180 g/m² in assembly.
Suitable for	Indoor and outdoor use
Shelf-life	12 month
Storage	Unopened and stored in dry and cool conditions (Between +5 and +25 °C)

Continues on the next page...

\*\* This information relates to

\* These values may vary depending on environmental factors such as temperature, moisture, and type of

substrates.

# TDS

## RAKENNUSKEMIA

fully cured product.

+358 - 19 - 457 4400 Kerkkolankatu HYVINKÄÄ, FII

Kerkkolankatu 17 05800 HYVINKÄÄ, FINLAND info@rakennuskemia.com www.rakennuskemia.com

#### COPYRIGHT NOTICE

Copyright © 2020,2021 Rakennuskemia Oy. All rights reserved. All materials contained in this document or in the attachments to this document are protected by copyright law and may not be reproduced, distributed, transmitted, displayed, published, broadcast or changed for any purpose whatsoever without the prior written permission of Rakennuskemia Oy, or in the case of third party materials, the owner of that content. You may not alter or remove any trademark, copyright or other notice from copies of the content.



## WTF® D4 WOOD GLUE

#### Updated: 23.01.2025

#### BENEFITS

- One component
- Easy to tool
- Water resistant D4
- Transparent after drying
- High end strength
- Fast drying time
- Resistant against high temperatures

#### **APPLICATIONS**

- Exterior use, exposed to weather factors but with adequate surface protection (e.g. layer of paint).
- Bonding of windows and door frames (also corner connections) which need to meet class D4 according to EN204.
- Bonding of wood, board, chipboard, veneer.
- Assembly glueing of soft wood.
- Construction bonding such as mortise and tenon joints, punches, etc.
- Stationary edge-banding with veneers, plastic laminates and solid wood strips
- Surface bonding of decor-finish film, HPL and CPL to chipboard, MDF and plywood.
- Bonding joints in boards and block bonding of softwood, hardwood and chipboard.

#### SURFACE PREPARATION

Substrates: many non-porous and porous substrates like wood, carton, laminate, etc.

**Nature:** The to be bonded materials should be flat and well fitting as well as clean, dry and free of dust and grease.

**Surface preparation:** Slightly grinding smooth non-porous surfaces can improve the adhesion. We recommend a preliminary adhesion test on any substrate.

#### USE

- Application method: Apply the adhesive with a notched trowel, brush or machine on one of the materials to be bonded. Join the parts together and clamp for 1 to 2 hours.
- Pressing times: if applicable. Curing time depends strongly on the used kind of wood, temperature, amount of adhesive and the porosity of the materials to be bonded. Minimum pressing times High-frequency bonding with longitudinal heating > 15 sec. and Dekor-finish 5 10 sec. Minimum pressing times assembly bondings: 8 15 min. Minimum pressing times bonding joints and block bonding: 10 15 min. Surface bonding of HPL/CPLin short cycle presses at 70°C: to plywood approx. 90 sec. and to chipboard approx. 45 sec.
- Cleaning: Before curing, D4 Wood Glue can be removed with water from substrates and tools. Cured D4 Wood Glue can only be removed mechanically.
- Note: When bonding certain woods such as beech and cherry discoloration may occur because of the variety of composition and pretreatment.
- Note: Do not dilute the adhesive.

For more information, see the safety data sheet

TDS

### RAKENNUSKEMIA

+358 - 19 - 457 4400 Kerkkolankatu 17 05800 HYVINKÄÄ, FINLAND info@rakennuskemia.com www.rakennuskemia.com

#### COPYRIGHT NOTICE

Copyright © 2020,2021 Rakennuskemia Oy. All rights reserved. All materials contained in this document or in the attachments to this document are protected by copyright law and may not be reproduced, distributed, transmitted, displayed, published, broadcast or changed for any purpose whatsoever without the prior written permission of Rakennuskemia Oy, or in the case of third party materials, the owner of that content. You may not alter or remove any trademark, copyright or other notice from copies of the content.